Acrylate Facade Paint EXTRA

Technical information sheet

2,5l / Item no.020623 / EAN 4016215020623
5l / Item no.020654 / EAN 4016215020654
10l / Item no.020708 / EAN 4016215020708

This weather-resistant façade paint impresses with its high opacity and an even, matt finish. It is UV-stable, impervious to driving rain and particularly resistant to external influences. Ideal for new and renovation coatings, it ensures long-lasting, well-maintained façades with a modern look.

- Matt coating with high opacity
- Weatherproof and UV-stable
- abrasion-resistant
- airless sprayable
- 1 litre for approx. 6 m² for a single coat on a smooth substrate

Area of application

Emulsion paint for weather-resistant, driving rain-proof facade coatings - non-yellowing, alkali-resistant and also suitable for interior use.

Preparation

For all mineral substrates (such as concrete, masonry, levelling compounds, cement, gypsum and lime plaster), firmly adhering emulsion paint coats. The substrate must be dry, clean, sound, evenly absorbent and free of dust and grease. Remove loose material and poorly adhering coats of paint from the substrate. Prime highly absorbent, sanding and chalking substrates with baufan Deep Primer LF. Repair cracks, holes and unevenness with a suitable baufan levelling compound (e.g. baufan exterior filler).

Processing

Stir well before use and apply with a roller, brush, paintbrush, flat brush or suitable spraying equipment. As a primer, the paint can be diluted with max. 10 % water. Apply undiluted as a top coat after the first coat of paint has dried. When coating larger areas, work wet-on-wet to avoid build-up. The paint should not be applied in direct sunlight, strong winds or where there is a risk of rain. Clean tools with water immediately after use. Drying time: approx. 5 hours under normal conditions (+20 °C, 65% relative humidity, moderately absorbent substrate); longer drying time under unfavourable conditions. Tinting: With a maximum of 10% universal tinting concentrates or full colour and tinting paint. Please observe the relevant technical information regarding light and weather fastness. Notes on airless spray application: Spray angle: 50° Nozzle: 0.023 - 0.027 Spray pressure: 120 - 180 bar

Consumption

Smooth surfaces/fine plaster grain → from 150 ml/m² Determine exact consumption quantity by test coating on the object.

Storage

Keep container tightly closed in a cool but frost-free place. If unopened and stored properly, shelf life is at least until: see batch label.

Notes

Processing temperature: +5 °C to +30 °C for material, circulating air and substrate Do not cover surfaces to be painted. Keep out of reach of children. Ensure adequate ventilation during application and drying. Do not inhale spray mist. Avoid eating, drinking and smoking while using the paint. Wear safety goggles. In case of contact with eyes or skin, rinse immediately with plenty of water. Do not allow to enter drains, waterways or soil. Only dispose of empty containers for recycling. Hazardous respirable droplets may be produced when spraying. Do not inhale aerosol or mist. Use combination filter A2/P2 when spraying.

Baufan Bauchemie Leipzig GmbH ■ Ludwig-Hupfeld-Straße 19 ■ 04178 Leipzig ■ Phone +49 (0)341 44655-0 ■ E-mail info@baufan.de ■ Internet www.baufan.com

Note:
All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.