

Silk Gloss Latex

Technical information sheet

2,5l / Item no.021736 / EAN 4016215021736

5l / Item no.021743 / EAN 4016215021743

10l / Item no.021750 / EAN 4016215021750



This high-quality latex paint gives surfaces an elegant, silky gloss finish and impresses with its high opacity. It is particularly hard-wearing, scrub-resistant and easy to clean - ideal for high-traffic areas. Suitable for indoor and outdoor use, it ensures long-lasting, well-maintained surfaces with a professional look.

- for highly durable coatings
- Silk-gloss surface finish
- Contrast ratio class 2 with a yield of 6.5 m²/l
- Wet abrasion resistance class 1 according to DIN EN 13300
- Gloss level: medium gloss
- Free from solvents, plasticisers and fogging-active substances
- airless sprayable
- High opacity

Area of application

Emulsion paint for interior and exterior wall and ceiling surfaces. Ideal for surfaces that need to be cleanable.

Preparation

For all mineral substrates (such as concrete, masonry, levelling compounds, cement, gypsum and lime plaster), plasterboard and other drywall, firmly adhering emulsion paint coats as well as woodchip, glass fabric and other paintable wallpaper and wall coverings. The substrate must be dry, clean, stable, evenly absorbent and free of dust and grease. Remove loose material, old wallpaper and poorly adhering paints from the substrate. Prime highly absorbent, sanding and chalking substrates with baufan Deep Primer LF. Repair cracks, holes and unevenness with a suitable baufan levelling compound.

Processing

Stir well before use and apply with a roller, brush, paintbrush, flat brush or suitable spraying equipment. As a primer, the paint can be diluted with max. 10 % water. Apply undiluted as a top coat after the first coat of paint has dried. When coating larger areas, work wet-on-wet to avoid build-up. Clean tools with water immediately after use. Drying time: approx. 5 hours under normal conditions (+20 °C, 65% relative humidity, moderately absorbent substrate); longer drying time under unfavourable conditions. Tinting: With a maximum of 10% universal tinting concentrates or solid tinting paint. Notes on airless spray application: Spray angle: 50° Nozzle: 0.023 - 0.027 Spray pressure: 120 - 180 bar

Consumption

Smooth surfaces/fine plaster grain → from 125 ml/m² Determine exact consumption quantity by applying a test coat to the object.

Storage

Keep container tightly closed in a cool but frost-free place. If unopened and stored properly, shelf life is at least until: see batch label.

Notes

Application temperature: +5 °C to +30 °C for material, circulating air and substrate Do not cover surfaces to be painted. Keep out of reach of children. Ensure adequate ventilation during application and drying. Do not inhale spray mist. Avoid eating, drinking and smoking while using the paint. Wear safety goggles. In case of contact with eyes or skin, rinse immediately with plenty of water. Do not allow to enter drains, waterways or soil. Only dispose of empty containers for recycling. caution! Hazardous respirable droplets may be produced when spraying. Do not inhale aerosol or mist. Use combination filter A2/P2 when spraying.

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.